

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C03C 13/06, 3/087 // A01G 31/02	A1	(11) International Publication Number: WO 96/00196 (43) International Publication Date: 4 January 1996 (04.01.96)
(21) International Application Number: PCT/DK95/00262 (22) International Filing Date: 23 June 1995 (23.06.95) (30) Priority Data: 0751/94 23 June 1994 (23.06.94) DK (71) Applicant (for all designated States except US): ROCKWOOL INTERNATIONAL A/S [DK/DK]; Hovedgaden 584, DK-2640 Hedehusene (DK). (72) Inventors; and (75) Inventors/Applicants (for US only): SØRENSEN, Lone, Møller [DK/DK]; Bistruphave 7 B, DK-3460 Birkerød (DK). JENSEN, Søren, Lund [DK/DK]; Tordenskjoldsgade 23, 2.th., DK-1055 Copenhagen K (DK). CHRISTENSEN, Vermund, Rust [DK/DK]; Søager 11, DK-4000 Roskilde (DK). GULDBERG, Marianne [DK/DK]; Neils Finsens Allé 55, DK-2860 Søborg (DK). (74) Agent: LEHMANN & REE A/S; Grundtvigsvej 37, DK-1864 Frederiksberg C (DK).		(81) Designated States: AM, AT, AT (Utility model), AU, BB, BG, BR, BY, CA, CH, CN, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, ES, FI, FI (Utility model), GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i>
(54) Title: THERMOSTABLE AND BIOLOGICALLY SOLUBLE FIBRE COMPOSITIONS (57) Abstract Thermostable and biologically soluble man-made vitreous fibres obtainable from a melt having a low liquidus temperature and a low crystallisation rate comprising SiO ₂ : 48-64 % by weight, Al ₂ O ₃ : 0.3-4 % by weight, FeO: 6-10 % by weight, CaO: 10-35 % by weight, MgO: 7-20 % by weight, Na ₂ O: 0-10 % by weight, K ₂ O: 0-6 % by weight, the ratio of (Na ₂ O + K ₂ O + 0.1CaO) to (MgO + FeO) being > 0.15 and (MgO + FeO) being greater than 14 % by weight and (Na ₂ + K ₂ O) being less than or equal to 10 % by weight.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

THERMOSTABLE AND BIOLOGICALLY SOLUBLE FIBRE COMPOSITIONS

The present invention relates to thermostable man-made vitreous fibres (MMV fibres) and more specifically to thermostable MMV fibres which are soluble in biological fluids. The present invention also relates to products, such as insulation products and plant growth media made from such fibres as well as to fibres useful for reinforcement or as fillers.

MMV fibre insulation products are widely used and have been commercial products for a long period of time. The insulation products are made from raw materials which are melted and spun into fibres. Such products also comprise a binder, which holds the fibres together. The binder is usually a phenol-formaldehyde resin or a urea-modified phenol-formaldehyde resin.

It is well known that rock and slag based fibre insulation products present the advantage compared to glass fibre insulations products that they exhibit a higher fire resistance, i.e. an improved thermostability. Typically, glass wool withstands temperatures up to around 650°C whereas stone wool is capable of withstanding temperatures up to about 1000°C. It is highly desirable to maintain this excellent property in any modification of the hitherto known rock or slag based fibre products.

Recently, more attention has been put to health issues associated with various fibrous materials, including MMV fibres. It is well known that inhalation of certain types of fibres such as asbestos fibres may lead to respiratory diseases, including lung cancer. It is believed that an important factor is the tendency of the asbestos fibres to remain in the lung for extended periods of time. Although there has not yet been provided any evidence of MMV fibres being the cause of respiratory or other diseases in man, it is desirable to provide MMV fibres with an increased dissolution rate in biological fluids in order to reduce their half-time in the lungs upon inhalation.

The concern for possible health effects of MMV fibres has been the reason for a number of investigations in the recent years. It is

believed that apart from the fibre dimensions, also the time of residence in the lung may be an important parameter for causing disease. The residence time is influenced by the physical clearance of the fibres from the lung and by the rate of dissolution of the fibres.

The rate of dissolution of fibres may be assessed in different ways. In in vitro measurements the fibres are subjected to the influence of artificial, physiological solutions (Gamble's solution, modified according to the disclosure in Scholze, H. Conradt.: An in vitro study of the chemical durability of siliceous fibres. Ann. Occ. Hyg. 31, p. 683-692, (1987)), believed to resemble the conditions in the lung fluids. The liquids used are all characterised in that they have a pH of 7.4-7.8. However, it is known from Carr, Ian: The Macrophage - A Review of Ultrastructure and Function. Academic Press, (1973), that the pH in the macrophages is lower, i.e. more acidic, than that of the lung fluid, resembled by the normally used liquids.

Recent published measurements of fibre durability, including in vivo measurements of the fibre dissolution in rat lungs indicate that this difference in pH may account for different rates of dissolution, and it has been found that the fibres, when sufficiently short, may be engulfed by the macrophages. This might explain the lower rate of dissolution observed for shorter glass wool fibres.

WO 89/12032 discloses inorganic fibre compositions among which some have passed the ASTM E-119 two hour fire test as well as exhibit low durabilities in physiological saline solutions, i.e. have high dissolution rates therein. The components of the prior art compositions may vary considerably. However, all the disclosed compositions are made from pure metal oxides or from less pure raw materials with addition of pure oxides which make the disclosed compositions very costly.

International patent application No. PCT/DK93/00435 describes a fiberisable composition which is thermostable and has a high dissolution rate in biological fluids and which consists essentially of

	SiO ₂	53.5 - 64 w/w%
	Al ₂ O ₃	≤ 4 w/w%
	CaO	10 - 20 w/w%
5	MgO	10 - 20 w/w%
	FeO	6.5 - 8 w/w%,

the total amount of FeO and Fe₂O₃ being calculated as FeO.

10 It is believed that the amount of magnesia and ferrous/ferric oxide components in a mineral composition has a significant influence on the thermostability of the MMV fibres. The ferrous/ferric oxide plays the important role of a crystal nucleating agent in the conversion of the fibre material from an amorphous condition to a
15 crystalline or pseudo crystalline state during external influence of heat, e.g. during fire. Accordingly, this provides certain restrictions on the minimum amount of ferrous/ferric oxide component present in the composition. It should be noted that MMV fibre material without ferrous or ferric oxide may be capable of with-
20 standing high temperatures which are reached by slow heat-up but not the fast heat-up resulting e.g. from external fire. When MMV fibre material is subjected to fire (sudden and/or fast heat-up), the structure of the material, i.e. the stone wool, is converted from an amorphous condition to a crystalline state.

25 Thus, the thermostability of MMV fibres depends on their ability to rapidly crystallize when they are exposed to the influence of sudden heat or fire, i.e. when they are subjected to the influence of temperatures of up to about 1000°C, such as temperatures of 700-
30 800°C. By undergoing a rapid crystallization the shrinkage of products made from such fibres is only minimal. A fibre capable of rapid crystallization is obtained by including a crystal nucleating agent in the fibre material.

35 MMV fibres, such as the fibres described in the above-mentioned international patent application, having a relatively high concentration of FeO tend to undergo a rapid crystallization when heated to temperatures of up to about 1000°C.

However, the tendency of such fibres to crystallize at such temperatures has an adverse effect on the properties of the melts from which such fibres are made.

- 5 In the production of MMV fibres the starting materials are heated to a sufficiently high temperature to form a melt which through gutters or the like is passed to a spinner in which the melt is spun into fibres.
- 10 Generally for rock based melt compositions an increasing content of MgO and FeO will raise the liquidus temperature. Furthermore, a FeO content of above 6% combined with a low Al_2O_3 content will cause high crystallization rate. Therefore substantial slag formation in the gutters and outlet of the furnace have been observed for com-
- 15 positions within the limits of the prior art (PCT/DK93/00435) which makes the melt less suitable for spinning.

For these compositions it has been necessary to heat the melt to a temperature of at least 200°C above the liquidus temperature of the melt, which is 50-100°C higher than in normal manufacturing conditions. The liquidus temperature is defined as the temperature at which a melt starts to crystallize when it is cooled.

20

The object of the invention is to provide MMV fibres which are obtainable from a melt having a relatively low liquidus temperature and a low crystallisation rate and thereby not creating substantial slag formation in the process, and which at the same time exhibit a good thermostability and a high dissolution rate in biological fluids.

25

30

The fibres of the invention comprise:

	SiO_2	48-64% by weight
	Al_2O_3	0.3-4% by weight
35	FeO	6-10% by weight
	CaO	10-35% by weight
	MgO	7-20% by weight
	Na_2O	0-10% by weight
	K_2O	0-6 % by weight

the total amount of FeO and Fe_2O_3 being calculated as FeO, the ratio of $(\text{Na}_2\text{O} + \text{K}_2\text{O} + 0.1 \cdot \text{CaO})$ to $(\text{MgO} + \text{FeO})$ being greater than 0.15, $(\text{MgO} + \text{FeO})$ being greater than 14 % by weight and $(\text{Na}_2\text{O} + \text{K}_2\text{O})$ being less than or equal to 10% by weight.

5

The invention is based on the discovery that both the liquidus temperature and the crystallisation rate of the melts for the production of fibres according to the invention is lowered to desirable respective levels by a broad range of compositions as long as the above relations are met. Thus, a relatively high concentration of alkali may be used or a relatively low concentration of MgO + FeO combined with an increased amount of CaO, or a combination of both. On the other hand, in order to maintain a high thermostability, the sum of MgO and FeO should be above 14% by weight.

15

In addition to the oxides mentioned above the fibres of the invention may contain other oxides, such as B_2O_3 , BaO, P_2O_5 , MnO_2 , ZrO_2 and TiO_2 .

20 In a preferred embodiment of the invention the alkali concentration, i.e. the sum of Na_2O and K_2O is equal to or greater than 4. Thus, the liquidus temperature is reduced with increasing concentrations of alkali. However, too high concentrations of alkali have a negative influence on the thermal stability.

25

Within a range of levels of alkali concentrations below a level of balance with the concentration of Al_2O_3 an increase in the concentrations of alkali causes an increase in the melt viscosity. At levels of alkali concentration higher than the level of balance a further increase in the concentration of alkali causes a reduction of the melt viscosity.

30

In another preferred embodiment of the invention the concentration of MgO is preferably between 7 and 10% by weight and the concentration of CaO preferably between 20 and 32% by weight. The higher the content of CaO, and preferably a CaO content of more than 19% by weight, more preferably of at least 20% by weight, having an upper limit of 35% by weight, preferably 32% by weight, works like the alkalis in reduction of the liquidus temperature, however, with a

35

somewhat lower effect per weight percentage. At the same time the lower MgO plus FeO content reduces the crystallisation rate.

According to another preferred embodiment of the invention, the
5 concentration of CaO is between 10 and 16% by weight while the concentration of alkali is larger than 4% by weight.

In order to obtain a viscosity which is particularly suitable for spinning, the melt should preferably contain from 48 to 60% by
10 weight of SiO₂.

It would be desirable to combine high concentrations of SiO₂ with very low concentrations of Al₂O₃, but since low Al₂O₃-containing raw materials are difficult to obtain it is preferred to use starting
15 materials having a content of SiO₂ in the lower end of the above-mentioned range. The Al₂O₃ content of the fibres of the invention should be above 0.3% by weight and preferably above 1.0% by weight in order to keep the costs of the raw materials within reasonable limits.

20 The composition of the melt used for the manufacture of MMV fibres according to the invention preferably contains the following oxides in such weight percentages that CaO + MgO + Na₂O + K₂O + BaO + B₂O₃ minus 2·Al₂O₃ is greater than 30.

25 The fibres of the invention may e.g. be prepared from the following naturally occurring raw materials:

	Quartz sand	about 36 %
30	Olivine sand	about 17 %
	Iron ore	about 12 %
and	Dolomite	about 11 %
	together with: Cement	about 12 %
35	and MMV fibre waste	about 12 %.

Examples of other raw materials are slags, glass, foundry sand, lime stone, magnesite, brucite, talc, serpentinite, pyroxenite and wollastonite.

The mineral composition of the present invention is particularly suitable for the manufacture of MMV fibres by the method disclosed e.g. in WO 92/06047.

- 5 For the manufacturing of fibres e.g. by this method a composition having a viscosity of approximately 15 poise at the working temperature is preferred. On the other hand a melt composition having a viscosity within the range of 4-15 poise at the working temperature is acceptable.

10

The invention further relates to a method of maintaining the high rate of dissolution in a biological fluid of a thermostable MMV fibre material, which method comprises the use of the MMV fibres as described above.

15

In the present specification and claims, the term "biological fluid" denotes physiological salt or saline solutions as well as any fluid present in vivo in mammals.

- 20 The MMV fibre material according to the invention exhibits a sintering temperature of at least 900°C, more preferably at least 1000°C.

The MMV fibre material according to the invention which is thermostable and has a high dissolution rate in biological fluids is
25 useful for thermal and/or acoustic insulation purposes or as a plant growing medium or substrate.

- The fibres are also useful as reinforcement fibres in various matrix materials such as plastics, rubber compositions and ceramics or as a
30 filler.

EXAMPLE

- 35 The dissolution rate and the thermostability of MMV fibres made from various compositions was determined as described below. The fibres were made by melting the raw materials in a cupola furnace, followed by spinning the fibre material into stone wool. Binder was not applied.

The constituents of each test composition is shown in Table 1. It is to be understood that in addition to the constituents mentioned in Table 1 each of the tested fibre compositions contained up to a total of 2 w/w% of other constituents (traces) forming part of the raw materials used. Such other constituents may include, for example, manganous oxide, chromium oxide, and various sulfur compounds. However, the percentages in Table 1 are standardised to a total of 100 w/w% of the listed constituents.

Tests 1-5 illustrate compositions according to the invention, whereas tests A-F are comparative compositions, test D-E being mentioned in PCT/DK93/00435.

TEST METHODS

Dimensions of the Fibre Samples

The samples were sieved, and the fraction below 63 μm was used for the tests.

For each sample, the fibre diameter distribution was determined, measuring the diameter and length of 200 individual fibres by means of an scanning electron microscope (1500 X magnification). The readings were used for calculating the specific surface of the fibre samples, taking into account the density of the fibres.

Measurements of Rate of Dissolution (Stationary Set-Up)

300 mg of fibres were placed in polyethylene bottles containing 500 ml of a modified Gamble's solution (i.e. with complexing agents) at pH 7.5. Once a day the pH was checked and if necessary adjusted by means of HCl.

The tests were carried out during a one week period. The bottles were kept in water bath at 37°C and shaken vigorously twice a day. Aliquots of the solution were taken out after one and four days and analysed for Si on an Perkin-Elmer Atomic Absorption Spectrophotometer.

The modified Gamble's solution, adjusted to pH 7.5 ± 0.2 , had the following composition:

	<u>g/l</u>
5	
MgCl ₂ ·6H ₂ O	0.212
NaCl	7.120
CaCl ₂ ·2H ₂ O	0.029
Na ₂ SO ₄	0.079
10 Na ₂ HPO ₄	0.148
NaHCO ₃	1.950
(Na ₂ -tartrate)·2H ₂ O	0.180
(Na ₃ -citrate)·2H ₂ O	0.152
90% Lactic acid	0.156
15 Glycine	0.118
Na-pyruvate	0.172
Formalin	1 ml

Calculations

20

Based on the dissolution of SiO₂ (network dissolution), the specific thickness dissolved was calculated and the rate of dissolution established (nm/day). The calculations were based on the SiO₂ content in the fibres, the specific surface and the dissolved amount

25

of Si.

Thermostability

30

The thermostability expressed as the sintering temperature of the fibre compositions 1-4 and A-F was established by the following method:

35

A sample (5 x 5 x 7.5 cm) of stone wool made of the fibre composition to be tested was placed in a furnace pre-heated to 700°C. After 0.5 hours exposure the shrinkage and the sintering of the sample was evaluated. The method was repeated each time with a fresh sample and a furnace temperature 50°C above the previous furnace temperature until the maximum furnace temperature, at which no sintering or no excessive shrinkage of the sample was observed, was determined.

The test results are shown in Table 2 below.

Table 1

5	Test No.	Composition, % by weight							
		SiO ₂	Al ₂ O ₃	TiO ₂	FeO	CaO	MgO	Na ₂ O	K ₂ O
10	1	55.6	4.0	0.8	6.8	13.9	12.8	0.6	5.4
	2	57.2	2,5	0.5	6.9	13.8	12.6	6.0	0.5
	3	50.7	2.9	0.2	6.7	25.7	10.1	3.0	0.6
	4	52.6	3.2	0.3	6.8	25.3	11.1	0.1	0.6
	5	55.0	2.1	0.2	7.5	25.6	8.4	0.8	0.3
15	A	52.2	4.4	0.3	8.1	29.5	4.4	0.1	1.0
	B	60.4	2.7	0.6	5.5	11.0	11.3	7.9	0.6
	C	53.0	3.1	0.5	5.1	28.7	8.2	0.7	0.6
	D	56.4	2.7	0.5	7.3	17.0	15.1	0.4	0.6
	E	46.8	13.2	2.9	6.3	17.2	9.6	2.8	1.2
	F	54.9	4.0	0.6	6.8	17.2	15.3	0.5	0.7
20									

Table 2

25	Test No.	Sintering temperature, °C	Dissolution, pH = 7.5*	Process Characteristics
25	1	1000	5.6	No tendency to slag formation
	2	1000	6.0	
	3	900	8.1	
	4	1000	9.2	
30	5	>1100	19.3	"
	A	750	3.7	"
	B	750	4.8	"
	C	800	6.1	"
	D	1100	13.0	Strong tendency
35	E	1050	3.0	
	F	1050	12.0	Strong tendency

* Dissolution rate of Si (nm/day) 1st-4th day

The comparative examples A-C all have a low liquidus temperature and a low crystallization rate and thereby a low tendency to slag formation due to either a relatively high content of alkali and/or high content of CaO and a relatively low concentration of MgO + FeO.
5 However, the thermostability of the comparative examples A-C are all low due to either a low content of FeO and/or a low content of MgO.

The comparative examples D and F both have a strong tendency to slagging due to the high content of (MgO + FeO) in combination with
10 the low content of alkali and/or CaO giving a relative high liquidus temperature and crystallisation rate. Due to the high content of MgO + FeO examples D and F both have excellent thermostability.

The comparative example E exhibits both excellent thermostability
15 due to the relative high content of (MgO + FeO) and a low tendency to slagging due to the high content of Al_2O_3 . However, due to the high content of Al_2O_3 the comparative example E has a rather low dissolution rate in biological fluids.

20 While specific embodiments of the invention have been described herein, others may practise the invention in any of the numerous ways which are suggested to one skilled in the art by this disclosure. Therefore, all such practice of invention is considered to be a part hereof which falls within the scope of the appended
25 claims.

30

35

CLAIMS

1. Thermostable MMV fibres exhibiting a high dissolution rate in biological fluids, characterized in that they comprise:

	SiO_2	48-64% by weight
	Al_2O_3	0.3-4% by weight
	FeO	6-10% by weight
10	CaO	10-35% by weight
	MgO	7-20% by weight
	Na_2O	0-10% by weight
	K_2O	0-6 % by weight

- 15 the total amount of FeO and Fe_2O_3 being calculated as FeO , the ratio of $(\text{Na}_2\text{O} + \text{K}_2\text{O} + 0.1 \cdot \text{CaO})$ to $(\text{MgO} + \text{FeO})$ being >0.15 and $(\text{MgO} + \text{FeO})$ being greater than 14% by weight and $(\text{Na}_2 + \text{K}_2\text{O})$ being less than or equal to 10% by weight.

- 20 2. Thermostable MMV fibres according to claim 1, characterized in that $\text{Na}_2\text{O} + \text{K}_2\text{O}$ is equal to or greater than 4.

3. Thermostable MMV fibres according to claim 1 or 2, characterized in that it contains the following oxides in such weight percentages that $\text{CaO} + \text{MgO} + \text{Na}_2\text{O} + \text{K}_2\text{O} + \text{BaO} + \text{B}_2\text{O}_3$ minus $2 \cdot \text{Al}_2\text{O}_3$ is greater than 30.

4. Thermostable MMV fibres according to any of the preceding claims, characterized in that the concentration of MgO is between 7 and 10% by weight.

5. Thermostable MMV fibres according to any of the preceding claims, characterized in that the concentration of CaO is between 20 and 32% by weight.

6. Thermostable MMV fibres according to any one of the preceding claims, characterized in that the concentration of (CaO) is between 10 and 16% by weight.

13

7. Thermostable MMV fibres according to any one of the preceding claims, characterized in that the concentration of $(\text{Na}_2\text{O} + \text{K}_2\text{O})$ is greater than 7% by weight.

5 8. Thermostable MMV fibres according to any of the preceding claims, characterized in that the concentration of SiO_2 is between 48 and 60% by weight.

10 9. Thermostable MMV fibres according to any one of the preceding claims, characterized in that the concentration of Al_2O_3 is between 1% and 4% by weight.

15 10. Use of MMV fibres according to any of claims 1-9 for thermal and/or acoustic insulation purposes.

11. Use of MMV fibres according to any of claims 1-9 as a plant growth medium or substrate.

20 12. Use of MMV fibres according to any of claims 1-9 for reinforcement purposes.

13. Use of MMV fibres according to any one of claim 1-9 as a filler.

25

30

35

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 95/00262

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C03C 13/06, C03C 3/087 // A01G 31/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C03C, A01G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 9322251 A1 (ISOVER SAINT-GOBAIN), 11 November 1993 (11.11.93), claim 1, abstract, table 1, ex. 3,4; table 4, ex. 9,10,11	1-4,8,10,12, 13
Y	--	11
Y	EP 0201426 A1 (ISOVER SAINT-GOBAIN), 17 December 1986 (17.12.86), figure 1, abstract	11
A	EP 0459897 A1 (ISOVER SAINT-GOBAIN), 4 December 1991 (04.12.91), abstract	1-13
	-- -----	

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

13 Sept 1995

Date of mailing of the international search report

04-10-1995

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

May Hallne
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/DK 95/00262

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO-A1-	9322251	11/11/93	NONE	
EP-A1-	0201426	17/12/86	SE-T3- 0201426	
			AU-B- 587820	31/08/89
			AU-A- 5648886	13/11/86
			FR-A,B- 2581503	14/11/86
			JP-A- 61254132	11/11/86
			KR-B- 9310536	28/10/93
			US-A- 4769277	06/09/88
			US-A- 4879172	07/11/89
EP-A1-	0459897	04/12/91	AT-T- 121378	15/05/95
			AU-B- 642493	21/10/93
			AU-A- 7731891	05/12/91
			CA-A- 2043699	02/12/91
			CN-A- 1059135	04/03/92
			DE-D- 69108981	00/00/00
			FR-A,B- 2662688	06/12/91
			JP-A- 4228455	18/08/92
			US-A- 5250488	05/10/93